

Product Specification - GEOWEB® GW20V Geocells

GENERAL

The GEOWEB geocell product is manufactured from textured, perforated strips of high density polyethylene that are bonded together to create a network of interconnected cells. The GEOWEB cells can be filled with topsoil, aggregate, concrete, recycled materials, or other infill material for geotechnical applications such as: 1) load support for unpaved and paved roads, railways, ports, heavy-duty pavements, container yard, and pads; 2) gravity and reinforced walls, reinforced slopes and fascia walls; and, 3) slope, channel, and geomembrane protection.

DIMENSIONS

Parameter	Units	Value
Cell Depth (Available in 4 Depths)	Inches (mm)	3 (75), 4 (100), 6 (150), 8 (200)
Cell Size (Length x Width +/- 10%)	Inches (mm)	8.8 x 10.2 (224 x 259)
Expanded Section Width	Cells	10
	Feet (m)	Varies: 7.7 to 9.2 (2.3 to 2.8)
Expanded Section Length	Cells	18, 21, 25, 29, or 34
	Feet (m)	Varies: 12 to 27.3 (3.7 to 8.3)

STRUCTURAL INTEGRITY AND SYSTEM PERFORMANCE

Parameter	Units	Value
<u>Minimum</u> Short Term Seam Peel Strength	lbf/in (N/cm)	≥ 80 (142)
Long-Term Seam Peel Strength (standard 4-inch sample width) ¹	lb (N)	160 (710)
Internal Junction Efficiency ²	%	≥ 100
Mechanical Junction Efficiency (ATRA Key Connection) ²	%	≥ 100
Peak Friction Angle Ratio (δ/ϕ) ³	Unitless	0.95

MATERIAL PROPERTIES

Parameter	Test Method	Units	Value
Polymer Density	ASTM D1505 or D792	lbs/ft ³ (g/cm ³)	58.4 - 60.2 (0.935 - 0.965)
Flexural Storage Modulus	ISO 6721	Mpa	≥ 800
Carbon Black Content ⁴	ASTM D1603	%	1.5 - 2.0
Sheet Thickness Prior to Texture	ASTM D5199	mil (mm)	50 (1.27), -5% +10%
Sheet Thickness After Texture	ASTM D5199	mil (mm)	60 (1.52), -5% +10%
Texture Density (Texture Type/Shape: Rhomboidal)	--	per/in ² (per/cm ²)	140 -200 (22 - 31)

DURABILITY

Parameter	Test Method	Units	Value
Environmental Stress Crack Resistance	ASTM D1693	hrs	> 5,000
Environmental Stress Crack Resistance (Accelerated Test)	ASTM D5397	hrs	> 400
Resistance to Oxidation ⁵	EN ISO 13438	yrs	≥ 100
Resistance to Weathering ⁶	EN 12224	%	100

Notes:

- 1) A 4.0 in. (100 mm) wide seam sample shall support a 160 lb (72.5 kg) load for a period of 7 days minimum in a temperature-controlled environment undergoing a temperature change on a 10 hour cycle from ambient room to 130° F (54° C). Ambient room temperature is per ASTM E 41.
- 2) Junction efficiency determined as a percentage of junction performance (EN ISO 13426-1) to perforated strip performance (EN ISO 10319).
- 3) Typical design value for granular infill material. Consult with manufacturer to confirm value for other types of infill materials.
- 4) Standard black HDPE strips. For tan/green GEOWEB, hindered amine light stabilizer (HALS) content will be 2.0% by weight of carrier.
- 5) Predicted to be durable for a minimum of 100 years in natural soil with a pH between 4 and 9 and at a soil temperature ≤ 25°C.
- 6) 100% of original tensile strength retained following exposure to intense UV radiation and accelerated weathering in accordance with EN 12224.



© 2024 Reynolds Presto Products, Inc. This specification is copyrighted and based on the use of Genuine Geoweb® manufactured by Reynolds Presto Products, Inc. (Presto Geosystems). Any use of this specification for any product other than that manufactured by Reynolds Presto Products, Inc. is strictly prohibited.



DISTRIBUTED BY:

ASP Enterprises, Quick Supply Co., Bowman Construction Supply & Cascade Geosynthetics are sister companies that serve customers from the Midwest, across the Rocky Mountains to the Pacific Northwest. Together we supply customers with a variety of environmental construction materials including erosion and sediment control, geosynthetics, stormwater management, drainage products, hardscapes and outdoor living, revegetation and soil amendments, waterproofing solutions and more.



We are full line distributors of environmental construction materials for all project types. Contact us for assistance with a project or a quote on products. From specification recommendations and project development to installation and completion, we're here to help with all of your site solution needs. Our warehouses are stocked with readily available inventory and we offer same and next-day deliveries.

ASP ENTERPRISES

aspent.com

salesasp@aspent.com

ST. LOUIS

1099 Cassens Industrial Ct.
St. Louis, MO 63026
636-343-4357

KANSAS CITY

5301 E 59th St.
Kansas City, MO 64130
816-554-1191

OMAHA

15263 Cooper St.
Omaha, NE 68138
402-861-8579

WICHITA

316-393-1554

WENTZVILLE

1906 E Service Rd. HWY 61 N
Wentzville, MO 63385
636-445-9090

QUICK SUPPLY CO.

quicksupplyco.com

salesquick@quicksupplyco.com

DES MOINES

6620 NW Toni Dr.
Des Moines, IA 50313
515-289-1271

BOWMAN CONSTRUCTION SUPPLY

bowmanconstructionsupply.com

salesbcs@bowmanconstructionsupply.com

DENVER

10801 E. 54th Ave.
Denver, CO 80239
303-696-8960

COLORADO SPRINGS

2445 Wayside Ct.
Colorado Springs, CO 80915
719-257-7840

LOVELAND

4495 Woods Ave.
Loveland, CO 80538
970-535-0863

CASCADE GEOSYNTHETICS

cascadageos.com

salescascade@cascadageos.com

PORTLAND

3610 N. Suttle Rd. Bldg B
Portland, OR 97217
971-339-1020

SALT LAKE CITY

425 N. Neil Armstrong Rd.
Salt Lake City, UT 84116
435-276-0820

**GEOSYNTHETICS | EROSION CONTROL | STORMWATER MANAGEMENT
REVEGETATION & SOIL AMENDMENTS | SEDIMENT CONTROL | HARDSCAPES**