



## PRODUCT DATA SHEET **CURLEX® II (.98)**

### DESCRIPTION

Curlex II .98 erosion control blanket (ECB) consists of a specific cut of naturally seed free Great Lakes Aspen curled wood excelsior with 80% six-inch fibers or greater fiber length. It is of consistent thickness with fibers evenly distributed throughout the entire area of the blanket. The top and bottom of each blanket is covered with degradable polypropylene netting. Curlex II .98 is also available as QuickGRASS® (green pigment). Curlex II .98 shall be manufactured in the U.S.A.

Curlex II .98 has a design soil loss ratio (event-based RUSLE C factor) of .022 and is typically suitable for slopes up to 1H:1V. Curlex II .98 is rated for channel flows up to 10.0 ft/s (3.1 m/s) and 2.5 lb/ft<sup>2</sup> (120 Pa) shear stress.

### PHYSICAL PROPERTIES

Curlex II .98 measurements at time of manufacturing:

<b>Width</b>	4.0 ft (1.2 m)	8.0 ft (2.4 m)	16.0 ft (4.9 m)
<b>Length</b>	90.0 ft (27.4 m)	90.0 ft (27.4 m)	90.0 ft (27.4 m)
<b>Area</b>	40.0 yd <sup>2</sup> (33.4 m <sup>2</sup> )	80.0 yd <sup>2</sup> (66.9 m <sup>2</sup> )	160.0 yd <sup>2</sup> (133.8 m <sup>2</sup> )
<b>Weight<sup>a</sup></b>	39.2 lb (17.8 kg)	78.4 lb (35.6 kg)	156.8 lb (71.2 kg)
<b>Fiber Count</b>	≈9,400 per yd <sup>2</sup> (≈11,280 per m <sup>2</sup> )	≈9,400 per yd <sup>2</sup> (≈11,280 per m <sup>2</sup> )	≈9,400 per yd <sup>2</sup> (≈11,280 per m <sup>2</sup> )
<b>Fiber Length (80% min.)</b>	≥6.0 in (≥15.2 cm)	≥6.0 in (≥15.2 cm)	≥6.0 in (≥15.2 cm)
<b>Mass per Unit Area (± 10%)</b>	0.98 lb/yd <sup>2</sup> (0.53 kg/m <sup>2</sup> )	0.98 lb/yd <sup>2</sup> (0.53 kg/m <sup>2</sup> )	0.98 lb/yd <sup>2</sup> (0.53 kg/m <sup>2</sup> )
<b>Net Openings</b>	1.0 in x 2.0 in (25.4 mm x 50.8 mm)	1.0 in x 2.0 in (25.4 mm x 50.8 mm)	1.0 in x 2.0 in (25.4 mm x 50.8 mm)

### TYPICAL INDEX VALUES

<u>Index Property</u>	<u>Test Method</u>	<u>Value</u>
Thickness	ASTM D 6525	0.251 in (6.38 mm)
Light Penetration	ASTM D 6567	16.6%
Resiliency	ASTM D 1777/ECTC	53%
Mass per Unit Area	ASTM D 6475	0.824 lb/yd <sup>2</sup> (0.447 kg/m <sup>2</sup> )
MD-Tensile Strength Max.	ASTM D 6818	134.4 lb/ft (1.96 kN/m)
TD-Tensile Strength Max.	ASTM D 6818	42.0 lb/ft (0.61 kN/m)
MD-Elongation	ASTM D 6818	26.9%
TD-Elongation	ASTM D 6818	23.8%
Swell	ECTC Procedure	56%
Water Absorption	ASTM D 1117/ECTC	279%
Bench-Scale Rain Splash	ASTM D 7101	SLR = 15.84 @ 2 in/hr <sup>b,c</sup>
Bench-Scale Rain Splash	ASTM D 7101	SLR = 19.32 @ 4 in/hr <sup>b,c</sup>
Bench-Scale Rain Splash	ASTM D 7101	SLR = 15.17 @ 6 in/hr <sup>b,c</sup>
Bench-Scale Shear	ASTM D 7207	2.60 lb/ft <sup>2</sup> @ 0.5 in soil loss <sup>c</sup>
Germination Improvement	ASTM D 7322	Pass

<sup>a</sup> Weight is based on a dry fiber weight basis at time of manufacture. Baseline moisture content of Great Lakes Aspen excelsior is 22%.

<sup>b</sup> SLR is the Soil Loss Ratio, as reported by NTPEP/AASHTO. <sup>c</sup> Bench-scale index values should not be used for design purposes.





## DISTRIBUTED BY:

ASP Enterprises, Quick Supply Co., Bowman Construction Supply & Cascade Geosynthetics are sister companies that serve customers from the Midwest, across the Rocky Mountains to the Pacific Northwest. Together we supply customers with a variety of environmental construction materials including erosion and sediment control, geosynthetics, stormwater management, drainage products, hardscapes and outdoor living, revegetation and soil amendments, waterproofing solutions and more.



We are full line distributors of environmental construction materials for all project types. Contact us for assistance with a project or a quote on products. From specification recommendations and project development to installation and completion, we're here to help with all of your site solution needs. Our warehouses are stocked with readily available inventory and we offer same and next-day deliveries.

### ASP ENTERPRISES

[aspent.com](http://aspent.com)

[salesasp@aspent.com](mailto:salesasp@aspent.com)

#### ST. LOUIS

1099 Cassens Industrial Ct.  
St. Louis, MO 63026  
636-343-4357

#### KANSAS CITY

5301 E 59th St.  
Kansas City, MO 64130  
816-554-1191

#### OMAHA

15263 Cooper St.  
Omaha, NE 68138  
402-861-8579

#### WICHITA

316-393-1554

#### WENTZVILLE

1906 E Service Rd. HWY 61 N  
Wentzville, MO 63385  
636-445-9090

### QUICK SUPPLY CO.

[quicksupplyco.com](http://quicksupplyco.com)

[salesquick@quicksupplyco.com](mailto:salesquick@quicksupplyco.com)

#### DES MOINES

6620 NW Toni Dr.  
Des Moines, IA 50313  
515-289-1271

### BOWMAN CONSTRUCTION SUPPLY

[bowmanconstructionsupply.com](http://bowmanconstructionsupply.com)

[salesbcs@bowmanconstructionsupply.com](mailto:salesbcs@bowmanconstructionsupply.com)

#### DENVER

10801 E. 54th Ave.  
Denver, CO 80239  
303-696-8960

#### COLORADO SPRINGS

2445 Wayside Ct.  
Colorado Springs, CO 80915  
719-257-7840

#### LOVELAND

4495 Woods Ave.  
Loveland, CO 80538  
970-535-0863

### CASCADE GEOSYNTHETICS

[cascadageos.com](http://cascadageos.com)

[salescascade@cascadageos.com](mailto:salescascade@cascadageos.com)

#### PORTLAND

3610 N. Suttle Rd. Bldg B  
Portland, OR 97217  
971-339-1020

#### SALT LAKE CITY

425 N. Neil Armstrong Rd.  
Salt Lake City, UT 84116  
435-276-0820

**GEOSYNTHETICS | EROSION CONTROL | STORMWATER MANAGEMENT  
REVEGETATION & SOIL AMENDMENTS | SEDIMENT CONTROL | HARDSCAPES**